

# RG-110 Flashing Compound

## Product Description

RG-110 Flashing Compound is formulated from acrylic based elastomeric resin, titanium dioxide and special reinforcing materials providing a long-lasting, durable, resilient patch. The cured patch is UV and water resistant with excellent resistance to mildew attack and weathering.

## Basic Use

Ideal for repairing metal roof seams, penetration and wall flashings, small holes, splits, cracks, blisters in built-up, modified bitumen, polyurethane foam and concrete.

## Limitations

Do not apply below 50°F (10°C) or when rain is forecast. Applications during periods of low temperatures or high humidity will extend dry time. Where ponding water conditions persist beyond 48 hours, corrective measures must be taken to eliminate ponding. Allow Flashing Compound to dry a minimum of four (4) hours before exposure to rain, heavy dew or temperatures below 50°F. If Flashing Compound is subjected to rain before it dries and some wash off occurs, it is essential to wash stained surfaces as soon as possible with warm soapy water. **KEEP FROM FREEZING.**

## Technical Data

Vehicle Base	Acrylic Based Resin
Weight per gallon	11.25 lbs
Solids by weight	64% +/- 2%
Solids by volume	52% +/- 2%
Viscosity @ 80°F (27°C)	Trowelable
pH	8.5 +/- .5
Specific gravity	1.35
Flash Point	None
VOC	< 50 g/l
Dry Film Thickness @25 sqft/gal or 30 lineal ft/gal	32 mils
Dry Time – set to touch	1 to 2 hours
To coat	24 to 48 hours
Solvent	water
Clean up	Warm soapy water

## Surface Preparation

Surfaces must be free of dirt, dust, loose paint, dried caulk, mastic, and other foreign matter that could prevent proper adhesion.

## Application

Apply with brush, trowel or putty knife. Product is ready to use and requires little or no mixing. **DO NOT THIN.** May be applied over damp, not wet, surfaces.

## Coverage

Coverage will vary depending on surface and size of area being patched. A thickness of 1/16" (1.6 mm) is generally sufficient, which represents an application rate of approximately 25 sq. ft./gal. or 30 lineal ft./gal. (1.63 L/s2.m).

## Maintenance

It is recommended that the coating installation be checked on a regular maintenance schedule. Small area touch ups can be made at any time following recommended application procedures.

## Technical Services

Technical advice on use of material for specific application and end use requirements is available from the manufacturer. Material Safety Data Sheet (MSDS) should be consulted for further information. This product is for industrial and professional use only.

## Packaging

5 gallon pails (18.9 liters)

## Warranty

This product is manufactured of good materials and by competent workmen. Seller's and manufacturer's only obligations shall be to replace such quantity of product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising from the use or the inability to use the product. Before using, user shall determine the suitability of the product for his/her intended use; and user assumes all risk and liability.